



BOLTS MARKINGS

METRIC					
	CLASS 4.6 400 Mpa Low Tensile Strength Carbon Steel	CLASS 8.8 825 Mpa High Tensile Strength Carbon Steel	CLASS 10.9 1034 Mpa High Tensile Strength Carbon Steel	CLASS 12.9 1200 Mpa High Tensile Strength Carbon Steel	
	G304 STAINLESS 700 Mpa Moderate Tensile Strength Stainless Steel	G316 STAINLESS 700 Mpa Moderate Tensile Strength Stainless Steel	G316 STAINLESS 800 Mpa High Tensile Strength Stainless Steel		
	IMPERIAL				
		GRADE 2 62 000 ibf/in ² Low Tensile Strength Carbon Steel	GRADE 5 120,000 ibf/in ² High Tensile Strength Carbon Steel	GRADE 8 150,000 ibf/in ² High Tensile Strength Carbon Steel	
G304 STAINLESS 101,000 ibf/in ² Moderate Tensile Strength Stainless Steel		G316 STAINLESS 101,000 ibf/in ² Moderate Tensile Strength Stainless Steel			
Refer to the «Imperial vs Metric Strength Chart» for strength comparisons					